

technical information

#3836

CRICSSM



"GREEN"
Coating Products

Ceramic Reflective Insulating Coating Systems

ProTek – DURAFINISHTM 100% ACRYLIC ELASTOMERIC CERAMIC INSULATING WALL COATING *Matte Finish*

PRODUCT DESCRIPTION

DURAFINISHTM is a 100% Acrylic, Elastomeric, Ceramic, waterproofing Wall Coating. A waterborne, latex-based, high build formula, DURAFINISHTM forms a thick, rubber-like ceramic shield of protection. DURAFINISHTM expands and contracts with varying hot and cold temperatures and resists thermal shock. DURAFINISHTM offers superior mildew resistance, ceramic insulation, high UV ray reflectivity, soundproofing and excellent adhesion to various types of materials. It is designed specifically as an insulating energy saving wall coating. DURAFINISHTM actually extends the life of walls. DURAFINISHTM offers a 20 YEAR LIMITED WARRANTY when applied as a two coat system per manufacturer's specifications. DURAFINISHTM is easy-to-apply and will eliminate costly maintenance, repairs and frequent repainting. It is a coating that will provide years and years of durable protection and outstanding beauty.

APPLICATION PROCEDURE

Stir well. Do not mix with other products or dilute with water. Surfaces must be clean, dry and free of oil, dirt and wax residues prior to application. Remove loose or flaking coatings with pressure washer. Clean surface with detergent using brush or pressure washer, rinse well and allow to dry. Prime surface, if necessary, using ProTek-ELASTOPRIMETM. DURAFINISHTM bonds to primed metal, other paints, masonry, wood, T1-11 and other building materials. Concrete walls must be properly sealed prior to application. ProTek-CRETESEALTM or ProTek-ELASTOPRIMETM will provide the best results when sealing concrete walls. After surface has been properly prepared, DURAFINISHTM can be applied by brush, 3/4" nap roller or with a 1 GPM airless sprayer or 60 PSI pot sprayer using a .027 inch tip (remove filters from sprayer). Avoid wet film buildup (applying product at less than 50 sq. ft. per gallon) as this may cause surface cracks and "skin-over".

WARRANTY COMPLIANCE INFORMATION:

DURAFINISHTM 20 YEAR LIMITED MATERIAL WARRANTY is for product ONLY. It applies to chipping, cracking and peeling ONLY. Labor is NOT covered by this warranty. The product is not guaranteed to stop or prevent leaks. Leaks must be repaired before applying any coating. The Warranty is available only when product is applied according to Manufacturer's Application Procedures and strict Material Requirement Specifications and a Warranty Registration is submitted to ProTek-USA within 90 days of coating application (forms supplied). MINIMUM SPREAD RATE: Optional Primer no more than 150 sq.ft./Gallon. DuraFinish MatteTM no more than 150 sq.ft./Gallon/Coat. Two (2) coats required. 20 dry mils required, if primer is used; 16 dry mils if primer is not used.

ProTek-USA, LLC 800-420-2998 Fax: 06-782-7532

SAFETY CONSIDERATIONS

Do not take internally. If product comes in contact with eyes, flush immediately with water and contact a physician for medical attention. Avoid prolonged contact with skin or breathing of spray mist. For quickest removal from skin, wash with water before product dries.

KEEP OUT OF REACH OF CHILDREN

PHYSICAL PROPERTIES

Reflectivity: ...81.7%+ white {slightly less when tinted in
Emissivity:93%+white (light earth tones or pastels
Lead and Chromate Free:Yes
Vehicle Type:.....100% Acrylic Copolymer Emulsion
Cures by:Evaporation
Color:User tintable – White, Deep & Clear Bases
Pigment Type:Universal Tint
Hiding:Excellent
Finish:Matte (also available in Satin)
Solids by Weight:68% +/- 2%
Solids by Volume:48% +/- 2%
V.O.C Emissions:81.6 grams/liter (.68lb/gal.)
UV Resistance:Exceptionally high
Fungus/Mildew Resistance:High
Fire Rating:...Class "A", "1" or "I" (*applies to "Flat" finish only)
Weight:12.1 lb. /gal (wet)
Viscosity:100 KU
Elongation:104% (cured sample)
Film thickness:12-16 wet mils = 5-6 dry mils/coat
@ 100-150 sq. ft/gal

Approximate Dry Times:

To touch:2-4 hours @ 77 ° F
To recoat:12 hours plus 50% R.H.
To fully cure:5 -7 days

Open Pot life:6-8 hours at 77°F/ 50% R.H.

Shelf life: 1 year @ 40° - 80° F

Clean up:Soap and water

SHIPPING, STORAGE, DISPOSAL

Shipping ID: Non-Flammable, Non-Toxic liquid

Disposal of Unused Product: Dispose of unused product in EPA approved non-hazardous waste processing facility. Do not pour into sewer or storm drains.

APPROXIMATE COVERAGE:

2 coats, each @ 100 to 150 sq.ft./gal. applied to...

... Weathered Wood, T1-11 siding, plywood, primed or galvanized metal, primed synthetic or aluminum siding, tin copper, asbestos, asphalt, urethane, polystyrene, Styrofoam, fiberglass, stucco, clay, adobe, brick, slate, concrete

Email: fbf@protek-usa.com Website: www.protek-sa.com